

Technische Daten 3pes561

Composition/Materialzusammensetzung 100 % PES

colour/ Farbe V 561 weiss

Weaving Thermo Bonded Non Woven

technical characteristics	testing method	unit	target value
1. Weight / Flächengewicht	DIN EN 29073-1		
1.1 Total / Gesamt		g/m ²	50 + 2
2. Thickness / Dicke	DIN EN ISO 5084	mm	0,3
3. Tensile strength / Höchstzugkraft	DIN EN 29073-2		
3.1 Warp direction / Kette		N/5cm	> 40
3.2 Weft direction / Schuss		N/5cm	> 14
4. Elongation at maximum force/ Dehnung	DIN EN 29073-2		
4.1 Warp direction / Kette		%	> 10
4.2 Weft-direction / Schuss		%	> 15
5. Luftdurchlässigkeit	ISO 9237	m ² xsec	1100
6. Temperature / Temperatur		°C	230

Information for Transport, Storage and Handling:

Transport and storage should be only carried out in horizontal position.

The goods should be stored indoor, dry and frost-free.

Protection against extreme climatical variations to avoid condensate is advisable.